

Standard Series Nickel-Cadmium VRE D 5500

Engineered for cycling applications Saft's VRE D 5500 cell ideally suits for a wide range of portable applications.

In addition, it is well adapted for applications requiring a permanent charge (C/20) at temperatures of up to + 35°C.

To meet customers' requirements, Saft provides custom-designed and standardized battery packs.

For your battery design and system needs, please contact Saft's engineers.

Applications

- Electric bicycles, scooters and wheelchairs
- Professional appliances
- Professional lighting
- Lawn and gardening tools
- Vacuum cleaners

Main advantages

- Super high capacity
- Fast charge
- Good storage ability
- Excellent cycling performance

Technology

- Sintered positive electrode
- Plastic bonded negative electrode

Temperature range in discharge

- 40°C to + 60°C

Storage

Recommended: + 5°C to + 25°C
Relative humidity: 65 ± 5 %



Electrical characteristics

Nominal voltage (V)	1.2
Typical capacity (mAh)*	5500
IEC minimum capacity (mAh)*	5000
IEC designation	KRHR 33/62
Impedance at 1000 Hz (m Ω)	<4

* Charge 16 h at C/10, discharge at C/5.

Dimensions

Diameter (mm)	32.15 ± 0.10
Height (mm)	58.2 ± 0.4
Top projection (mm)	1.4 ± 0.4
Top flat area diameter (mm)	5.6 ± 0.1
Weight (g)	150

Dimensions are given for bare cells.

Charge conditions

Rate	Time (h)	Temp. (°C)	Charge current (mA)
Fast*	~ 1	+ 10 to + 40	up to 5000
Standard	16	+ 5 to + 50	500
Trickle**			150

* End of charge cut-off is requested: -dV or dT°C/dt.

** Trickle charge follows fast charge.

Maximum discharge current

Continuous (A) at + 20°C	50
Peak (A) at + 20°C*	150

* Peak duration: 0.3 second - final discharge voltage 0.6 volt./cell.




saft


Typical performances

For graphs shown, C is the IEC₅ capacity.


Dimensions are in mm.




Charge at 5 A




Discharge at different rates after charge at C/10



Discharge at different rates after charge at C



Capacity change during cycling at 10 A discharge, after full charge



Data are given for single cells.
Please consult Saft for utilization
of cell outside this datasheet.

Data in this document are subject to change
without notice and become contractual only
after written confirmation by Saft.

Saft Rechargeable Battery Systems

12, rue Sadi Carnot
93170 Bagnole - France
Tel.: +33 1 49 93 19 18
Fax: +33 1 49 93 19 68
Email: rbs.info@saftbatteries.com

www.saftbatteries.com

